



TEST REPORT

Ø 4.7 mm LIGNOLOC® with head

MEASURED VALUES* LIGNOLOC® WITH HEAD

	Average Value	Minimum Value	Maximum Value
Tensile strength nail head (> 10 measured values):	1840 N	1561 N	1966 N
Flexural strength Myk (> 10 measured values):	3005 Nmm	2716 Nmm	3316 Nmm
System test withdrawal - and head pull through values (> 5 measured values): Douglas fir on 3 layer board	1139 N	912 N	1445 N

* BECK internal test results

FASTENER DATA

Diameter	4.7 mm 0.185"
Length	58 mm 2 5/16"
Head	6.3 mm 0.248"
Material	compressed beech wood
Coil-capacity	100 nails
Collation	15° Coil LIGNOLOC®
Tool	FASCO® F60 CN15-PS90-H LIGNOLOC®

LIGNOLOC® WITH HEAD

The next development stage of the **LIGNOLOC®** wooden nail technology: the wooden nail with a head for façade construction. It has a blunt anti-splitting point and is suitable for the most common softwood façades as well as a variety of other applications, both indoors and outdoors, such as privacy screens, garden houses, garden pavilions, room dividers, etc.